

Stable Mat Luxury (SH)

Stable Mat Luxury is a 4.5 cm thick mat for lying areas, made from rubber granules bonded with polyurethane. It is designed for stables, outdoor stables and loose housing. It is made from recycled tyre rubber granules (ELT) bonded with polyurethane and compacted under high pressure. Its weight holds it down on the stable floor. A high underside profile insulates the mat from the cold concrete. The mat is resilient, very abrasion-resistant and slip-resistant even when wet.

The mats are laid without adhesive in a random bond pattern on a load-bearing, largely level base, such as concrete, concrete block paving or gravel grids filled with chippings. The area needs an edge restraint around its entire perimeter. In a stable, the walls provide this restraint. Unabsorbed urine must not be allowed to stand on the mats. It can be absorbed by bedding on the mats or in a specially bedded corner where the horse urinates. Alternatively, the horse can urinate in an open paddock. The lying area remains bedded.

Product data

Colour	Brick red	Weight	39 kg/piece = 39 kg/m²
Installation	Random bond	Conversion	1 m² = 1 piece
External dimensions	1000 x 1000 x 45 mm	factor: Laid size	100 x 100 x 4,5 cm 1,00 m²

Properties




Colour Brick red

Brick red is a classic building colour, the red of bricks and roof tiles. As a familiar tone it fits in anywhere in the townscape. A red pigmented binder binds the black rubber granules from tyre recycling and coats the granules as it does so. Depending on compaction, black may show through in places. Under load the coating may wear, first giving a salt and pepper look and, with heavy use or over time, wearing away completely.




Material

Cleaned, fine-to-medium recycled rubber granules with a granule size of 0.8–2.5 mm are the starting material for the product. The granules are produced by processing and recycling end-of-life tyres (ELT) and are made up of natural rubber (NR) and styrene-butadiene rubber (SBR). A polyurethane (PU) binder holds the granules together; it is clear in the black and anthracite versions, whereas in the coloured versions a pigmented binder forms a layer of colour around the black granules, which remain black on the inside. The surface is finely textured.



Installation

In a random bond, the tiles are laid loose and closely butted together without any connection between them. The rows are offset irregularly. As a result, no four tile corners meet at a single point, and the joints are staggered from row to row. The tiles' own weight and friction against the substrate limit lateral movement. Repeated loading and temperature changes can nevertheless cause the tiles to shift gradually. An edge restraint or wall limits this movement and helps to stop the joints opening up.



Underside

A profile of hollow, square feet approx. 15 mm high, linked by narrow ribs, is moulded into the underside. This leaves a continuous void between tile and substrate in which liquid can run off along the gradient and air can circulate. The profile compresses elastically under load. It is laid on a firm, load-bearing substrate. Please refer to the installation instructions.

Stable Mat Luxury (SH)

Properties



Efl

Normally flammable.



UV-stabilised

ELT granules are UV-stabilised. Some coating shades may change slightly outdoors.



Indoor and sheltered outdoor use

For indoor and sheltered outdoor areas. Avoid standing water and prolonged saturation.



Harmful substance limits met

Meets EU limits for harmful substances. Initial rubber odour diminishes.

Technical data

The key technical properties of WARCO products are rated on a scale of 1 to 5. This allows products intended for the same application to be compared directly. The relevant product page explains how each rating is determined.

Shock absorption and vibration damping, footstep sound reduction – Rating 3: marked damping

Abrasion resistance – Rating 5: highest rating (BS 7188)

Water permeability (BS EN 12616) – Rating 2: infiltration up to 10 mm/h (10 l/(m²·h))

Thermal insulation – Rating 4: thermal conductivity approximately 0.09 W/(m·K)

Slip resistance (BS EN 16165) – Rating 3: mean acceptance angle approx. 15°, R10 classification

Dynamic friction class DS (BS EN 14041) – Rating 2: dynamic coefficient of friction approx. 0.38

Compressive strength – Rating 4: permanent indentation of approximately 0.25 mm after 24 hours' recovery (BS 7188)

Apparent density – Rating 4: 900 to 1,000 kg/m³

WARCO SAFETY FLOORING LTD

8 Blackstock Mews
London N4 2BT

WARCO Gallery

Klemmhof 9
67433 Neustadt an der Weinstraße
Please arrange an appointment

Technical Consultation

T: 0117 205 0269

E: info@warco-tiles.com
W: www.warco-tiles.com