


Indoor Dog Sports Flooring (XT)

Indoor dog sports flooring is a continuous, abrasion-resistant surface for agility halls and training areas. It is installed loose, either as a single layer or as a sandwich system with functional tiles XX. The integrated jigsaw interlock connects the tiles securely and creates a virtually invisible hairline joint.

The wear layer made of EPDM rubber granules ensures a consistent surface, while the base layer of recycled ELT rubber granules provides impact absorption. The surface is slip-resistant, paw-friendly and thermally insulating. Its structure limits moisture penetration and supports easy cleaning with standard methods.



Product data

Colour	Terracotta	Weight	3.65 kg/piece = 18.34 kg/m²
Fixing system	Optimised jigsaw interlock without bevel	Conversion	1 m² = 5.03 piece
Dimensions	485 x 485 x 18 mm	Usable dimensions	44,6 x 44,6 x 1,8 cm

Properties



Colour Terracotta

Terra cotta blends warm browns and red-browns into a natural-looking surface inspired by Mediterranean clay and earth tones.

Material

This product has a two-layer construction. The wear layer, approximately 2 mm thick, consists of newly produced, permanently coloured EPDM granules (Ethylene Propylene Diene Monomer) bound with UV-stabilised polyurethane. The wear layer has a closed surface. The base layer is made from cleaned black recycled tyre rubber granules (ELT) of fine grain size, bound with polyurethane. ELT stands for "End of Life Tyres" and refers to granules produced from recycled tyres. The base layer is manufactured with a high compaction level.

Indoor Dog Sports Flooring (XT)

Characteristics



Indoor and Sheltered Outdoor Areas

Suitable for indoor and sheltered outdoor areas.
Avoid waterlogging and continuous moisture exposure.



Cfl-s1

Reaction to fire according to EN 13501-1: Cfl-s1
Limited contribution to fire. Low smoke production.



Colourfast and UV-resistant

The surface made of EPDM rubber granules is colourfast and long-term UV-resistant (sun).



Toxicologically safe

No impermissible pollutant emissions,
initial rubber odour dissipates over time.

Comparative values

Comparing technical data on a scale from 1 to 5 offers a practical way to objectively assess the relevant properties of WARCO products, making it easier to find the most suitable product for the intended application. Detailed information on the scale values and their calculation is available on the product detail page.

Compressive strength - Scale value 4 = approx. 0.25 mm residual dent after 24 hours of unloading (BS 7188)

Abrasion resistance – Resistance to abrasive wear – Scale value 3 = "very good" (BS 7188)

Thermal insulation – Scale value 2 = Thermal conductivity approx. 0.12 W/(m·K)

Slip resistance class DS (EN 14041) - Scale value 2 = Coefficient of friction approx. 0.38

Slip resistance (EN 16165) – Scale value 3 = mean acceptance angle approx. 15°, group R10

Water Permeability (EN 12616) – Rating 2 = Infiltration up to 10 mm/h (10 l/h/m²)

Apparent density - scale value 4 = 900 to 1000 kg/m³

Shock, vibration, and impact sound insulation – Scale value 1 = noticeable damping

Michael Schladt
WARCO Bodenbeläge
Andergasse 17
67434 Neustadt an der
Weinstraße

WARCO Gallery
Klemmhof 9
67433 Neustadt an der Weinstraße
Terminvereinbarung erforderlich.

Fachberatung
06321 9152391

E-Mail: info@warco.eu
web: www.warco.eu